

Via Predazzi, 48 24030 Carvico (BG) - Italy policrom@policrom.it Switch board: +39 035 4382411 www.policrom.it Fax: 035794679

POLIMPRESS

technical data sheet

DESCRIPTION	APPLICATION	FEATURES
White nonwoven polyester fiber embossed, manufactured with spunbonded technology	Developed for the automatic cleaning systems of the impression cylinders	The polyester structure and the particular calendering process ensures a minimal lint
CLEANING SIDE		

INSTRUCTIONS OF USE

Cleaning surface on the outside of the roll

PHYSICAL AND MECHANICAL PROPERTIES

Prop	erty	Test method	Unit	Nominal values
Composition	Polyester fibres	-	%	100
Colour		-	-	White
Weigth		EDANA 40.3-90	g/m²	70
Nominal thickness		EDANA 30.5-99	mm	0.270
Tensile strength	Machine Direction	EDANA 20.2-89	N/5cm	170
	Cross Direction			160
Elongation at break	Machine Direction	EDANA 20.2-89	%	25
	Cross Direction			30
Absorption	Water	EDANA 10.4-02	%	150

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.