



POLIPRINT INKJET SOLVY

technical data sheet

DESCRIPTION	APPLICATION	FEATURES
Clear, biaxially oriented PET treated on one side for ink-jet printing using solvent /ecosolvent inks	<ul style="list-style-type: none"> • Specific for wide format printing • Suitable for backlite applications 	<ul style="list-style-type: none"> • High dimensional stability • Excellent ink adhesion • Fast drying

PHYSICAL AND MECHANICAL PROPERTIES

Property		Test method	Unit	Nominal values
Nominal thickness		ASTM D 374	micron	100
Tensile strength	Machine Direction	ASTM D 882	daN/mm ²	20
Elongation at break	Machine Direction	ASTM D 882	%	145
Surface resistivity	20°C / 50% H.R.	Internal method 05	Ohms / cm	< 10 ¹¹

THERMAL PROPERTIES

Property		Test method	Unit	Nominal values
Shrinkage at 150°/30'	Machine Direction	ASTM 1204-08	%	1.6
	Cross Direction			0.3

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

T325 Rev.01nl 14/03/2019