



POLIPRINT LASER BASIC

technical data sheet

| DESCRIPTION | APPLICATION | FEATURES |
|---|--|---|
| Clear biaxially oriented PET film with paper interleaving | For black and white copiers when using the bypass feeder | <ul style="list-style-type: none"> • High dimensional stability • Optimal adhesion of ink |

PHYSICAL AND MECHANICAL PROPERTIES

| Property | | Test method | Unit | Nominal values |
|----------------------------|--------------------------|-------------|---------------------|----------------|
| Nominal thickness | | ASTM D 374 | micron | 100 |
| Tensile strength | Machine Direction | ASTM D 882 | daN/mm ² | 20 |
| Elongation at break | Machine Direction | ASTM D 882 | % | 140 |

THERMAL PROPERTIES

| Property | | Test method | Unit | Nominal values |
|------------------------------|--------------------------|--------------|------|----------------|
| Shrinkage at 150°/30' | Machine Direction | ASTM 1204-08 | % | < 1.6 |
| | Cross Direction | | | < 0.6 |

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

T359 Rev.01nl 14/03/2019