



POLIPRINT LASER

technical data sheet

DESCRIPTION	APPLICATION	FEATURES
Clear, heat stabilized PET film	For black and white copiers when using an automatic feeding system	<ul style="list-style-type: none"> • Very high dimensional stability • Excellent bonding of toner • Optimal for application in automatic equipment

PHYSICAL AND MECHANICAL PROPERTIES

Property		Test method	Unit	Nominal values
<i>Nominal thickness</i>		ASTM D 374	micron	100
<i>Tensile strength</i>	<i>Machine Direction</i>	ASTM D 882	daN/mm ²	21
<i>Elongation at break</i>	<i>Machine Direction</i>	ASTM D 882	%	150

THERMAL PROPERTIES

Property		Test method	Unit	Nominal values
<i>Shrinkage at 150°/30'</i>	<i>Machine Direction</i>	ASTM 1204-08	%	< 0.7
	<i>Cross Direction</i>			< 0.5

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

T358 Rev.01nl 14/03/2019