

Via Predazzi, 48 24030 Carvico (BG) - Italy policrom@policrom.it Switch board: +39 035 4382411 www.policrom.it Fax: 035794679

TEAR-OFF BLUE

technical data sheet

DESCRIPTION	APPLICATION	FEATURES
Non-woven rolls made of polyester fibers and wood pulp: width 290 mm pre-cut at 370 mm by	Developed for industrial manual cleaning	StrongSoft
400 pieces		Resistant to solvents

PHYSICAL AND MECHANICAL PROPERTIES					
Property		Test method	Unit	Nominal values	
Composition	Polyester fibres	- %	47		
	Wood pulp			53	
Colour		-	-	Blue	
Weigth		EDANA 40.3-90	g/m²	70	
Nominal thickness		EDANA 30.5-99	mm	0.250	
Tensile strength	Machine Direction	EDANA 20.2-89	N/5cm	210	
	Cross Direction			50	
Elongation	Machine Direction	EDANA 20.2-89	%	22	
	Cross Direction			100	
Absorption	Water	EDANA 10.4-02	%	400	

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

T097 Rev.01nl 23/10/2019