



## POLIBACK

### *technical data sheet*

DESCRIPTION	APPLICATION	FEATURES
Clear biaxially oriented PET film, coated to bond with liquid polymers	Base film used to produce flexographic plates with liquid photopolymer resins	Specific treatment which guarantees an excellent bonding of photopolymer resins

### INSTRUCTIONS OF USE

Not recommended for outdoor use

### PHYSICAL AND MECHANICAL PROPERTIES

Property		Test method	Unit	Nominal values	
<b>Nominal thickness</b>		ASTM D 374	mm	125	175
<b>Tensile strength</b>	<b>Machine Direction</b>	ASTM D 882	daN/mm <sup>2</sup>	21	21
<b>Elongation at break</b>	<b>Machine Direction</b>	ASTM D 882	%	140	150

*The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.*

*T209 Rev.01nl 14/03/2019*