




POLICOAT

technical data sheet

DESCRIPTION	APPLICATION	FEATURES
Polymeric translucent self-adhesive varnishing plate	Developed for indirect zones or full table off-set printing with both acrylic and U.V. varnishes	<ul style="list-style-type: none"> • Translucent • Satin surface • Self-adhesive • Resistant to the most common solvents used in printing
		Polymers Adhesive layer Protective film

INSTRUCTIONS OF USE

Base film to be coated with release layer before use

PHYSICAL AND MECHANICAL PROPERTIES

Property	Test method	Unit	Nominal values	
Nominal thickness	ASTM D 374	mm	0.53	0.68
Colour	-	-	Clear	
Translucent	-	-	Yes	
Hardness	Internal method 06	shore A	99°	
Shear resistance			> 40	
Adhesion strength			6 - 12	
Tensile strength <i>Machine Direction</i>	ASTM D 882	daN/mm ²	20	

WARNING: The properties may change in case of storage over 8 months after the date of arrival

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

T1760 Rev.01nl 25/09/2019