



## ELASTODUR ANTIGLARE AG10

manufactured in Japan by **KIMOTO Co., LTD**

### technical data sheet

DESCRIPTION	APPLICATION	FEATURES
PET film for graphic overlay (Cover) with anti scratch treatment on the top side	Developed as an overlay for the production of flexible switches and membrane keyboards	<ul style="list-style-type: none"> <li>• Good dimensional stability</li> <li>• Optimal flatness</li> <li>• Embossable</li> <li>• Gloss antiglare finish</li> <li>• One side scratch resistant</li> <li>• One side treated for screen printing and UV inkjet inks</li> </ul>
	<p><i>Suggested inks: Marabu MSW 171, MSW 180, MSW, MSW 932, MSW 980, MSW 981, UVSW 170, UVSW 180, UVSW 932, UVSW 980</i></p> <p>PRINTABLE SIDE IS PROTECTED WITH A LINER</p>	

### PHYSICAL AND MECHANICAL PROPERTIES

Property		Test method	Unit	Nominal values	
<b>Nominal thickness</b>		ASTM D 1186	micron	125	188
<b>Total thickness</b>		ASTM D 374	micron	135 (±10%)	198 (±10%)
<b>Tensile strength</b>	<b>Machine Direction</b>	ASTM D 882	daN/mm <sup>2</sup>	16.5	18.6
<b>Elongation at break</b>	<b>Machine Direction</b>	ASTM D 882	%	101.0	88.6
<b>Tape adhesive</b>		ASTM 3002	/100	100	100
<b>Film hardness by pencil test</b>		ASTM D3363	-	3H	3H
<b>Switch life</b>		300g; 10,000times/1hr	million flexes	> 5	> 5

### CHEMICAL PROPERTIES

Property	Test method	Unit	Nominal values
<b>Chemical resistance</b>	DIN 42115	-	Resistant to: Alcohols Dilute Acids Dilute Alkalis Esters Hydrocarbons Ketones Household Cleaning agents
<b>Moisture vapour transmission rate (MVTR)</b>	RTM 607	g/m <sup>2</sup> in 24 hours	2.6
<b>Oxygen transmission rate</b>	RTM 608	ml/m <sup>2</sup> in 24 hours	5.3

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.

Rev.01Inl 03/11/2021

## THERMAL PROPERTIES

Property		Test method	Unit	Nominal values
Coefficient of thermal expansion	Machine Direction	ASTM E794-85	cm/cm/°C	19 x 10 <sup>-6</sup>
	Cross Direction			16 x 10 <sup>-6</sup>
Shrinkage at 120°/30'	Machine Direction	ASTM D1204	%	< 0.2
	Cross Direction			< 0.1
Maximum and minimum long term use		Kimoto method	°C	-40 - 85

## ELECTRICAL PROPERTIES

Property		Test method	Unit	Nominal values
Volume resistivity		ASTM D257 and D2305 @ 25 °C	Ω/m	10 <sup>18</sup>
Surface resistivity	20°C / 50% H.R.	JIS-K-6911	Ω/cm	2.0 x 10 <sup>15</sup>
Dissipation factor		ASTM D150 @ 1kHz, 25 °C	-	0.005
Dielectric strength		ASTM D149 1/4" electrode 500V/sec in 25C dry air	kV	18

## OPTICAL PROPERTIES

Property		Test method	Unit	Nominal values
Total transmission		ASTM D1003	%	≥ 90
Haze		ASTM D1003	%	10 ± 2
Glossness	Angle test 60°	ASTM D523	%	< 100
Yellowness index		ASTM D2244	%	< 2

*The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.*

Rev.01Inl 03/11/2021